

Pebble-Flex® NP Skid Resistance Testing



ASTM C 1028

Sample ID: Aqua Flex 2

Dry, as Received

	Calibrate	Neolite
Average Force	38.50	44.25
Raw Coeff/Frict	0.75	0.87
Correction	0.11	0.11
Cor. Coeff/Frict.	0.86	0.97

Wet, as Received

	Calibrate	Neolite
Average Force	24.75	41.67
Raw Coeff/Frict	0.48	0.82
Correction	0.03	0.03
Cor. Coeff/Frict.	0.51	0.84

Dry, as Renovated

	Calibrate	Neolite
Average Force	39.25	43.83
Raw Coeff/Frict	0.77	0.86
Correction	0.09	0.09
Cor. Coeff/Frict.	0.86	0.95

Wet, as Renovated

	Calibrate	Neolite
Average Force	27.25	41.67
Raw Coeff/Frict	0.53	0.81
Correction	-0.02	-0.02
Cor. Coeff/Frict.	0.51	0.79

End of Report